



SIZE	T		E		E ₁		B		B ₁		P	S	α	β	CTR. DIA.	LEADS	T.P.I.
	IDEAL	TOL.	IDEAL	TOL.	IDEAL	TOL.	IDEAL	TOL.	IDEAL	TOL.							
58	2.094	±.015	2.054	±.015	2.048	±.015	2.104	±.015	2.295	±.025	1.754	.110 +.008 -.007	59°24'	5°50'	.500	10	1.50
63	2.344	±.015	2.304	±.015	2.298	±.015	2.354	±.015	2.545	±.025	2.004	.110 +.008 -.007	49°30'	6°15'	.500	10	1.25
66	2.454	±.015	2.414	±.015	2.408	±.015	2.464	±.015	2.655	±.025	2.114	.110 +.008 -.007	49°30'	5°58'	.500	10	1.25
70	2.610	±.015	2.570	±.015	2.564	±.015	2.620	±.015	2.810	±.025	2.270	.110 +.008 -.007	49°30'	5°37'	.500	10	1.25

- TOP AND SIDE SEALING SURFACE SHOULD BE FREE OF IRREGULARITIES TO A .274 DEPTH.
- PROPER FUNCTION OF CLOSURE REQUIRES THAT "E₁", "E", "T" & "B" DIAMETERS TO BE AS LITTLE OUT-OF-ROUND AS POSSIBLE AND THE LATTER THREE DIAMETERS BE PERPENDICULAR TO THE TOP OF FINISH. THE MAX. AND MIN. AVERAGES OF THESE DIAMETERS SHOULD BE AS CLOSE TO "IDEAL" AS POSSIBLE.
- PROPER CAM-OFF OF CLOSURE REQUIRES THAT THE THREADS PROJECT .020 +.003/- .002 OUT FROM THE 'E' DIA. BUT NEVER TO EXCEED THE 'B' DIA. THREAD PROFILE MUST BE WELL DEFINED AND WITHIN THE .020R +.003/- .002 AND THREAD ROOT RADII MUST NOT EXCEED .010.
- CROSS HATCHED AREA SHOWS CONTOUR TO BE CLEARED BY THE TOP OF GLASS FINISH.
- CONTOUR BELOW .274 MUST CLEAR CAP LIMITS SHOWN BY CROSS-HATCHED AREAS ABOVE .410 DIMENSION. WHERE MAXIMUM CONTAINER GRIPABILITY IS NECESSARY, THE CONTOUR BELOW .274 CAN FOLLOW THE OPTIONAL BEAD CONTOUR. IT IS RECOMMENDED THAT THE OPTIONAL BEAD CONSTRUCTION BE SPECIFIED FOR QUART SIZE AND LARGER WHERE IMPROVED CONTAINER GRIPABILITY IS NECESSARY.
- OPTIONAL - THIS AREA AS SPECIFIED MAY BE FILLED IN WITH GLASS NOT TO EXCEED THE THREAD PROJECTION.
- A LEVEL TOP FINISH IS IDEAL. MAXIMUM SADDLE IS .010" WITHIN 180°. CORRECTIONS SHOULD BE MADE IF A GLASS LOT CHECK SHOWS IT "RUNNING TOWARD MAX. SADDLES".
- OPTIONAL - FOR RELIEF OF MOLD OPENINGS. THREAD PROJECTION MAY BE DEPRESSED AT THE PARTING LINE. MAXIMUM ALLOWABLE DEPRESSION IS .005 PER SIDE FROM THE AVERAGE OF ACTUAL THREAD PROJECTIONS MEASURED ON A 6° ARC ON EITHER SIDE OF THE PARTING LINE.
- THE .432 DIMENSION REPRESENTS THE DISTANCE FROM TOP OF SEALING SURFACE DOWN TO HORIZONTAL LINE TANGENT TO BOTTOM SWING OF .062 RADIUS.
- "B" SPECIFICATION TO BE MAINTAINED TO .250 DOWN. BELOW THIS POINT A SLIGHTLY UNDER MINIMUM "B" IS ACCEPTABLE. HOWEVER THE MAXIMUM SPECIFICATION CANNOT BE EXCEEDED.
- VERTICAL DIMENSIONS WITH ASTERISKS (*) DENOTE THE GAGING DEPTHS FOR THE "E₁", "E", "T", & "B" DIAMETERS.
- PARTING LINE OFFSET AT .075 MIN. DEPTH MAY BE UP TO .010 ON A SIDE WITH .015 MAX. PER DIAMETER I.E. AMOUNT ON ONE SIDE ADDED TO AMOUNT ON OTHER SIDE SAME DIAMETER CAN BE EQUAL TO OR LESS THAN .015. AN OVERHANG OF THE .075 MIN. SECTION OUTSIDE OF THE "E" DIAMETER IS NOT PERMITTED.
- SECTION OF FINISH DENOTED BY HEAVY BLACK LINE IS TO BE FORMED IN A ONE PIECE "SLEEVE" OR "GUIDE RING". NO SEAMS OR PARTING LINES PERMITTED.
- TANGENT β = $\frac{\text{LEAD}}{\pi(\text{MEAN BETWEEN MEAN 'T' AND MEAN 'E'})}$
- "E" DIAMETER IS MEASURED AT THIS LOCATION AND REPRESENTS ENTIRE "E" HEIGHT. THEREFORE IT MUST BE AS VERTICAL AS POSSIBLE WITHOUT IRREGULARITIES THAT INFLUENCE "E" DIA. MEASUREMENTS.

THIS OFFICIAL GLASS PACKAGING INSTITUTE PRINT CONSTITUTES ONE IN A SERIES OF VOLUNTARY STANDARDS INTENDED TO PROVIDE A BASIS FOR ACHIEVING COMPATIBILITY AND INTERCHANGEABILITY BETWEEN MANUFACTURERS AND USERS OF GLASS CONTAINERS AND CLOSURES THEREFOR. THE USER SHOULD BE AWARE THAT OTHER CONTAINER AND CLOSURE DESIGNS MAY DIFFER FROM THIS VOLUNTARY STANDARD, AND IT IS THE USER'S RESPONSIBILITY TO MAKE THE FINAL DETERMINATION AS TO DESIGN AND COMPATIBILITY. GPI ASSUMES NO RESPONSIBILITY FOR EITHER THE USE OR INTERPRETATION OF THE STANDARD, FOR IT BEING CURRENT, OR FOR THE DETERMINATION WHETHER ANY PARTICULAR MANUFACTURER'S PRODUCT CONFORMS TO THE STANDARD. THIS DRAWING CONTAINS INFORMATION TAKEN FROM ONE OR MORE PRINTS OF THE GLASS PACKAGING INSTITUTE (GPI). GPI OWNS ALL RIGHT, TITLE AND INTEREST IN THE COPYRIGHTS TO THIS DRAWING AND TO THESE PRINTS. GPI REQUIRES THAT YOU NOT REPRODUCE THIS DRAWING FOR OR DISTRIBUTE THIS DRAWING TO ANY THIRD PARTY WITHOUT GPI'S WRITTEN CONSENT. ANY INQUIRIES OR SUGGESTIONS CONCERNING THIS STANDARD CAN BE ADDRESSED TO THE GLASS PACKAGING INSTITUTE, WASHINGTON D.C. AT WWW.GPI.ORG.

COPYRIGHT © GPI 1999

Edward A. Grant CHAIRMAN	PRINTED AND DISTRIBUTED AS A VOLUNTARY STANDARD BY GLASS PACKAGING INSTITUTE COMMITTEE ON DESIGN AND SPECIFICATIONS	APPROVED FOR PUBLICATION 10-12-99	SUPERSEDES DWG. NO.
	GLASS FINISH NUMBER 2220	GPI DWG. NO. 22200	
58,63,66 & 70 mm PRESS ON TWIST OFF FINISH			